

WOOD FLOOR - SEALING SYSTEMS

PREMIUM QUALITY
MADE IN GERMANY



WOOD PRIMER

WATER BASED QUICK DRY WOOD FLOOR SEALANT

PROPERTIES

WOOD PRIMER is an acrylic emulsion that seals all types of real wood flooring and provides optimal protection without changing the original structure of the wood. WOOD PRIMER is the ideal basis for further coating with WOOD SATIN FINISH or WOOD FINISH. WOOD PRIMER seals the floor against water, stains, and dirt and ensures that the coating is long lasting.

- Solids content 20 %
- No risk of individual wood elements gluing together
- Dries quickly within 60 minutes
- High Yield - about 15-20 m² per liter

This one-component system is easily applied with a clean professional wax cover (Wischwiesel) or Floor-Finish coating mop.

This high quality product seals the floor against water, stains, dirt and ensures a lasting hold of the coating.

SATIN-EFFECT

APPLICATION

Preparing the ground:

Remove dust from the floor with a synthetic acrylic mop and, if necessary, remove chewing gum and adhesive residue. First grind the coat with an ABRASIV HI-PRO pad then regrinding with a 60's or 80's grid pad and finally use the 120's grid pad for fine tuning. Vacuum the floor and wipe clean and dry until the last dust is removed. Check if the soil absorbs water. If yes, apply a maximum of 2 layers of WOOD PRIMER, if not, you can start directly with the coating of WOOD FINISH or WOOD SATIN FINISH.

Apply the seal:

Shake well before opening. Apply 1 liter per approx. 15 m² WOOD PRIMER with a clean professional wax cover (Wischwiesel) or Floor-Finish Coating Mop. Work at a steady pace and overlap in the grain direction of the wood. Allow the first layer to dry for at least 1 hour before applying another layer. In moist ambient conditions, a longer drying time is required. Apply a second layer, if necessary after drying the first layer. Grinding of the first layer is only necessary if a swelling of fibers has occurred or if the layer has dried for more than 6 hours. In this case, grind the floor with a 120's grip pad or ABRASIV HI-PRO pad. After grinding, always thoroughly vacuum and wipe. Depending on the surface quality 1-2 layers are necessary. After complete drying of WOOD PRIMER can be continued with the coating with WOOD FINISH or WOOD SATIN FINISH.


Note: Provide sufficient ventilation support during all phases of the floor coating process.

Check material compatibility before applying.

We accept no liability for damage caused by improper use.



UL classified slip resistant



pH-value in concentrate

7,7-8,7

0 2 4 6 8 10 12 14

Containers

5 L


ART.-NO.

01079-05

- Before always read the indications and product information.
- For commercial / industrial use only!!
- Reusable containers

- **Type:** Acrylic emulsion
- **Form:** Impermeable liquid
- **Fragrance:** Mild
- **Color:** White
- **Drying time:** 60 minutes
- **Solids:** 20%
- **Slip resistance:** UL classified slip resistant
- **Yield:** ca. 15 m²/liter

MFMA
approved



ARCORA® INTERNATIONAL

Marsstraße 9 • 85609 Aschheim near Munich - Germany
Fon: +49 (0)89 -14 33 29 30 • Fax: +49 (0)89 - 14 33 29 329

www.arcora-group.com
info@arcora.de